

**MARKED-UP VERSION OF  
ENGLISH TRANSLATION OF  
INTERNATIONAL APPLICATION  
AS ORIGINALLY FILED**

DESCRIPTION

LAMINATION-TYPE RESISTANCE ELEMENT

BACKGROUND OF THE INVENTION

1. ~~Technical~~ Field of the Invention

[0001] —The present invention relates to a lamination-type resistance element and more particularly to a lamination-type resistance element in which internal electrodes are disposed inside a laminated sinter so as to enable fine adjustment of a resistance value.

2. Description of the Related ~~Background~~ Art

[0002] —To date, resistance elements such as PTC thermistors and NTC thermistors have been used for temperature compensation and temperature detection. Among such resistance elements, there is a lamination-type resistance element that can be mounted on a printed-circuit board, etc. Hereinafter, ~~a plurality of~~ examples of related lamination-type resistance elements are ~~is~~ described.

[0003] —Fig. 7 is a sectional view showing a first related example wherein ~~and~~ the resistance element is an NTC thermistor.

[0004] —In a lamination-type thermistor 1 shown in Fig. 7, first internal electrodes 4a and 4b and second internal electrodes 5a and 5b are ~~provided~~ ~~contained~~ inside a laminated sinter 3 in which a plurality of thermistor layers 2 are

integrally sintered. External electrodes 7 and ~~8~~<sup>9</sup> are ~~provided~~<sup>formed</sup> on the outer surface and more ~~specifically~~<sup>concretely</sup> on both end portions of the laminated sinter 3.

[0005] —One end portion of the first internal electrode 4a and one end portion of the second internal electrode 5a face each other on the same ~~planar~~ <sup>plane</sup> surface with a gap 6a therebetween. The other end portion of the first internal electrode 4a is electrically connected to the external electrode 7 and the other end portion of the second internal electrode 4b is electrically connected to the external electrode 8.

[0006] —Furthermore, one end portion of the first internal electrode 4b and one end portion of the second internal electrode 5b face each other on the same ~~planar~~ <sup>plane</sup> surface with a gap 6b therebetween. The other end portion of the first internal electrode 4b is electrically connected to the external electrode 7 and the other end portion of the second internal electrode 5b is electrically connected to the external electrode 8.

[0007] —The gaps 6a and the gaps 6b are alternately disposed along the lamination direction of the plurality of thermistor layers 2 inside the laminated sinter 3. Furthermore, the gaps 6a and the gaps 6b are ~~arranged~~<sup>formed</sup> at different locations in the direction that is substantially perpendicular to the lamination direction of the laminated sinter 3.

[0008] —Fig. 8 is a sectional view showing a second

related example and, in the same way as in Fig. 7, the resistance element is an NTC thermistor.

[0009] —In a lamination-type NTC thermistor 11 shown in Fig. 8, first internal electrodes 14a and second internal electrodes 14b are ~~provided~~~~contained~~ inside a laminated sinter 13 in which a plurality of thermistor layers 12 are integrally sintered. Furthermore, internal electrodes 16 are ~~arranged~~~~formed~~ so as to face the first internal electrodes 14a and second internal electrodes 14b through a thermistor layer 12. External electrodes 17 and 18 are ~~provided~~~~formed~~ on the outer surface of the laminated sinter 12 and more ~~specifically~~~~concretely~~ on both end portions.

[0010] —One end portion of the first internal electrode 14a and one end portion of the second internal electrode 14b are ~~arranged~~~~formed~~ so as to face each other on the same plane with a gap 15 therebetween. The other end portion of the first internal electrode 14a is electrically connected to the external electrode 17 and the other end portion of the second internal electrode 14b is electrically connected to the external electrode 18.

[0011] —The internal electrode 16 is a no-connection-type internal electrode, both end portions of which are not ~~extended~~~~led~~ out to the outer surface of the laminated sinter 13 and which are ~~is~~ not connected to the external electrodes 17 and 18.

[0012] —The resistance value of the first related lamination-type resistance element is determined by the size of the gap 6a between ~~formed by~~ the first internal electrode 4a

and the second internal electrode 5a, the size of the gap 6b ~~between formed by~~ the first internal electrode 4b and the second internal electrode 5b, and the overlapping area between the first internal electrode 4a and the second internal electrode 5b and the space therebetween.

[0013] —Furthermore, the resistance value of the second related lamination-type resistance element is determined by the size of the gap 15 ~~between formed by~~ the first internal electrode 14a and the second internal electrode 14b, the overlapping area between the first internal electrode 14a and the no-connection-type internal electrode 16 and the space therebetween, and the overlapping area between the second internal electrode 14b and the no-connection-type internal electrode 16 and the space therebetween.

[0014] —In Japanese Unexamined Patent Application Publication No. 2000-124008~~the following Patent Document 3~~, a third related lamination-type resistance~~resonance~~ element is disclosed. In a resistance element disclosed in Japanese Unexamined Patent Application Publication No. 2000-124008~~Document 3~~, inside a negative-characteristic thermistor element, first and second internal electrodes are disposed so as to lie on top of one another with a thermistor element layer therebetween, the internal electrode is extended~~led~~ out to one end of the negative-characteristic thermistor element, and the other internal electrode is extended~~led~~ out to the other end. Then, the first and second external electrodes are arranged~~formed~~ at both ends of the thermistor element. Furthermore, a resistor layer made~~formed~~ of a resistive

material that is different from the material ~~defining~~~~constituting~~ the thermistor element is laminated on the thermistor element. Then, a pair of internal electrodes, one end of each facing one end of the other with a gap therebetween on the same plane, are provided~~formed~~ inside of the resistor layer. One of the internal electrodes is electrically connected to the first external electrode and the other is electrically connected to the second external electrode.

[0015] —Here, the resistance value can be set by adjustment of not only material characteristics and the shape of the above-described resistor~~resistor~~ layer, but also the pattern of a pair of electrodes inside the resonator layer, and thus, the freedom of setting the resistance value can be increased.

[0016] —Furthermore, in Japanese Unexamined Utility Model Registration Application Publication No. 6-34201~~the following Patent Document 4~~, an NTC thermistor as a lamination-type resistance element according to ~~of~~ a fourth example is disclosed. That is, an NTC thermistor in which a plurality of pairs of internal electrodes, the inner end of one of the pair facing the inner end of the other with a gap therebetween on the same plane, are provided~~contained~~ inside a lamination-type resistor. Here, in each pair of internal electrodes, one internal electrode is electrically connected to a first external electrode provided~~contained~~ on one end surface of the resistor and the other internal electrode is electrically connected to a second external electrode

~~provided~~~~formed~~ on the other end surface of the resistor. Then, when seen from a direction perpendicular to the upper surface of the resistor, in each of the plurality of pairs, the one internal electrode and the other internal electrode are disposed so as not to lie on top of one another. In this NTC thermistor, since the resistance value is determined by the size of a gap between a pair of internal electrodes disposed on the same plane, it is possible to reduce variations of the resistance value.

~~Patent Document 1: Japanese Unexamined Patent Application  
Publication No. 05-243007~~

~~Patent Document 2: Japanese Unexamined Patent Application  
Publication No. 10-247601~~

~~Patent Document 3: Japanese Unexamined Patent Application  
Publication No. 2000-124008~~

~~Patent Document 4: Japanese Unexamined Utility Model  
Registration Application Publication No. 6-34201~~

#### ~~Disclosure of Invention~~

[0017] —When the resistance value is adjusted in the first and second lamination-type resistance elements, the number of laminations of each internal electrode is increased or reduced. However, in the case of adjustment of the resistance value, in the first related example, since the number of internal electrodes 4a, 4b, 5a, and 5b facing each other through a thermistor layer 2 is increased or reduced, the range of change of the resistance value is wide and fine adjustment of the resistance value is difficult. In the

second related example, the number of units ~~madeformed~~ of internal electrodes 14a and 14b and internal electrodes 16 facing each other through a thermistor 12 is increased or decreased. Accordingly, the range of change of the resistance value is also wide and fine adjustment of the resistance value is difficult.

[0018] —On the other hand, in the lamination-type resistance element of the third related example, since the resistor layer is ~~madeformed~~ using a material different from a negative-characteristic thermistor element, the manufacturing process becomes complicated and, as a matter of course, the cost increases. Furthermore, since the thickness of the resistor layer is required to be sufficiently smaller than the thickness of the thermistor element, the design of the resistor and the internal electrodes are naturally restricted. Therefore, reduction in the resistance and fine adjustment of the resistance value are difficult.

[0019] —Furthermore, in an NTC thermistor described in the above-described Japanese Unexamined Utility Model Registration Application Publication No. 6-34201, reduction in the resistance is limited~~Patent Document 4~~, although variations of the resistance value can be reduced,~~reduction in the resistance is limited~~. When the size of the gap is reduced for each pair of internal electrodes disposed with a gap therebetween on the same plane, it is possible to decrease the resistance value. However, when the gap is reduced, since a short circuit becomes likely to occur, reduction in the resistance is limited.



#### SUMMARY OF THE INVENTION

[0020] — In ~~order to overcome the~~consideration of the  
~~above problems described above, preferred embodiment~~of the  
~~related technology, it is an object of the present invention~~  
~~to~~provide a lamination-type resistance element having a  
structure in which fine adjustment of the resistance value can  
be made in the lamination-type resistance element using a  
laminated sinter having internal electrodes.

[0021] — According to a ~~preferred embodiment~~broad aspect  
of the present invention, it is possible to provide a  
lamination-type resistance element ~~including~~comprising a  
laminated sinter having a plurality of ceramic resistance  
layers and a plurality of internal electrodes laminated  
therein, ~~+~~ and a first external electrode and a second external  
electrode ~~arranged~~formed on the outer surface of the laminated  
sinter. In the lamination-type resistance element, the  
plurality of internal electrodes ~~includes~~contains a plurality  
of internal electrodes of a first group and a plurality of  
internal electrodes of a second group, the plurality of  
internal electrodes of the first group ~~including~~containing a  
resistance unit in which at least two internal electrodes are  
disposed so as to face each other through the ceramic  
resistance layer, one end of the resistance unit being  
electrically connected to the first external electrode, and  
the other end being electrically connected to the second  
external electrode. ~~The , and the~~ internal electrodes of the  
second group ~~include~~containing a plurality of pairs of

internal electrodes, one end of each facing one end of the other with a gap therebetween on the same plane inside the laminated sinter, one internal electrode in each pair being electrically connected to the first external electrode, and the other being electrically connected to the second external electrode.

[0022] —In a specific preferred embodiment~~aspect~~ of a lamination-type resistance element according to the present preferred embodiment~~invention~~, the plurality of gaps of the second group is arranged~~formed~~ so as to lie on top of one another in the lamination direction in the laminated sinter.

[0023] —In another specific preferred embodiment~~aspect~~ of a lamination-type resistance element according to the present invention, each of the internal electrodes of the first group includes~~contains~~ a first divided internal electrode electrically connected to the first external electrode and a second divided internal electrode electrically connected to the second external electrode and one end of the first divided internal electrode and one end of the second divided internal electrode face each other with a gap therebetween on the same plane. Regarding~~and, regarding~~ the internal electrodes of each pair of the second internal electrode group, when the internal electrode electrically connected to the first external electrode is made a third internal electrode and the other internal electrode electrically connected to the second external electrode is made a fourth internal electrode, the topmost gap ~~which is the closest to the second group among the gaps~~ of the first group

is aligned with the bottommost gap ~~which is the closest to the first group among the gaps between the third and fourth internal electrodes of the second group that are disposed so as to lie on top of one another in the lamination direction.~~

[0024] —The structure of the above-described internal electrodes of the first group can be variously modified in the present invention.

[0025] —That is, in another specific preferred embodiment ~~aspect~~ of the present invention, a plurality of pairs of first and second divided internal electrodes are laminated and the gaps between adjacent ~~neighboring~~ pairs of electrodes in the lamination direction are provided ~~formed~~ at different locations when seen from one side in the lamination direction.

[0026] —Furthermore, in another specific preferred embodiment ~~aspect~~ of a lamination-type resistance element according to the present invention, in the internal electrodes of the first group, a no-connection-type internal electrode disposed on top of the first and second divided internal electrodes through a ceramic resistance layer is further provided ~~contained~~.

[0027] —In another specific preferred embodiment ~~aspect~~ of a lamination-type resistance element according to the present invention, the internal electrodes of a first group includes ~~contains~~ the first internal electrode electrically connected to the first external electrode and a second internal electrode electrically connected to the second external electrode, and the first and second internal

electrodes are disposed so as to lie on top of one another through a ceramic layer disposed therebetween.

[0028] —The above-described three lamination-type resistance elements in which the structures of the first internal electrodes are different from each other can be described as the following first to third preferred embodiments.

[0029] —A lamination-type resistance element as a first preferred embodiment of the present invention ~~includes~~~~comprises~~ a laminated sinter having a plurality of ceramic resistance layers and a plurality of internal electrodes laminated therein, ~~and~~ a first external electrode and a second external electrode ~~provided~~~~formed~~ on the outer surface of the laminated sinter. In the lamination-type resistance element, the internal electrodes ~~include~~~~contain~~ internal electrodes of a first group and internal electrodes of a second group, wherein the internal electrodes of a first group each ~~include~~~~contain~~ a first internal electrode and a second internal electrode, ~~one end of each being arranged~~~~formed~~ so as to face one end of the other with a gap therebetween on the same plane inside the laminated sinter and the other ends being connected to the first external electrode and the second external electrode, respectively, and neighboring gaps between the first and second internal electrodes in the lamination direction of the laminated sinter are ~~arranged~~~~formed~~ at different locations when seen from the lamination direction of the laminated sinter. The internal electrodes of, and the second group include third internal

electrodes and fourth internal electrodes, one end of each facing one end of the other with a gap therebetween on the same plane inside the laminated sinter and the other ends being connected to the first external ~~of the second group contain a pair of a third internal electrode and the second external a fourth internal~~ electrode one end of each facing one end of the other with a gap therebetween on the same plane inside the laminated sinter and the other ends being connected to the first external electrode and the second external electrode, respectively, and the gaps between ~~formed by~~ the third internal electrodes and fourth internal electrodes are at the same location along the lamination direction of the laminated sinter.

[0030] —Furthermore, a second preferred embodiment ~~means~~ for solving the problems described above is a lamination-type resistance element including ~~comprising~~ a laminated sinter having a plurality of ceramic resistance layers and a plurality of internal electrodes laminated therein, ~~+~~ and a first external electrode and a second external electrode provided ~~formed~~ on the outer surface of the laminated sinter. In the lamination-type resistance element, the internal electrodes include ~~contain~~ internal electrodes of a first group and internal electrodes of a second group, wherein the internal electrodes of the first group each include ~~contain~~ a first internal electrode and a second internal electrode one end of each being arranged ~~formed~~ so as to face one end of the other with a gap therebetween on the same plane inside the laminated sinter and the other ends being connected to the

first external electrode and the second external electrode, respectively, and a no-connection-type internal electrode which is ~~arranged~~<sup>formed</sup> so as to lie on top of the first internal electrode and the second internal electrode through the ceramic resistance layer in the lamination direction of the laminated sinter and which is not connected to the first and second external electrodes. ~~The , and the~~ internal electrodes of the second group each ~~includes~~<sup>contain</sup> a third internal electrode and a fourth internal electrode, one end of each facing one end of the other with a gap therebetween on the same plane inside the laminated sinter and the other ends being connected to the first external electrode and the second external electrode, respectively, and the gaps ~~between~~<sup>formed</sup> by the third internal electrodes and fourth internal electrodes are at the same location along the lamination direction of the laminated sinter.

[0031] —A third ~~preferred embodiment~~<sup>means</sup> is a lamination-type resistance element ~~including~~<sup>comprising</sup> a laminated sinter having a plurality of ceramic resistance layers and a plurality of internal electrodes laminated therein, ~~+~~ and a first external electrode and a second external electrode ~~provided~~<sup>formed</sup> on the outer surface of the laminated sinter. In the lamination-type resistance element, the internal electrodes ~~include~~<sup>contain</sup> internal electrodes of a first group and internal electrodes of a second group, the internal electrodes of the first group each ~~includes~~<sup>contain</sup> a first internal electrode connected to the first external electrode and a second internal electrode connected to the

second external electrode which face each other through the ceramic resistance layer. ~~The , and the~~ internal electrodes of the second group each ~~includes~~contain a third internal electrode and a fourth internal electrode, one end of each facing one end of the other with a gap therebetween on the same plane inside the laminated sinter and the other ends being connected to the first external electrode and the second external electrode, respectively, and the gaps ~~between~~formed by the third internal electrodes and fourth internal electrodes are at the same location along the lamination direction of the laminate sinter.

[0032]       —In a lamination-type resistance element of the preferred embodiments of the present invention, fine adjustment of the resistance value can be made by ~~providing~~forming internal electrodes of a second group inside a laminated sinter. That is, in a plurality of pairs of internal electrodes ~~defining~~constituting the internal electrodes of the second group, the internal electrodes of each pair are disposed with a gap therebetween on the same plane inside the laminated sinter. Since the resistance value determined by the gap is small, fine adjustment of the resistance value of the lamination-type resistance element can be made by changing the size of the gap in the plurality of pairs of internal electrodes and the number of pairs in the plurality of pairs of electrodes. That is, fine adjustment of the resistance value can be made by adjustment of the portion where the internal electrodes of the second group are ~~located~~constituted without greatly ~~affecting~~affected the

resistance value to be determined by the portion where the internal electrodes of the first group are located constituted.

[0033] —Furthermore, since it is possible to design a laminated sinter, that is, to design and set the resistance value in the same process as the technology for laminating ceramic resistance layers and internal electrodes, fine adjustment of the resistance value can be easily made.

[0034] Other features, elements, steps, characteristics and advantages of the present invention will become more apparent from the following detailed description of preferred embodiments of the present invention with reference to the attached drawings.

#### Brief Description of the Drawings BRIEF DESCRIPTION OF THE DRAWINGS

[0035] —Fig. 1 is a sectional view showing a first preferred embodiment of a lamination-type resistance element of the present invention.

[0036] —Fig. 2 is a sectional view showing a second preferred embodiment of a lamination-type resistance element of the present invention.

[0037] —Fig. 3 is a sectional view showing a third preferred embodiment of a lamination-type resistance element of the present invention.

[0038] —Fig. 4 is a front sectional view showing a modified example of a lamination-type resistance element for describing the process for making fine adjustment of the resistance value by using a lamination-type resistance element



of the present invention.

[0039] ——— Fig. 5 is a front sectional view of a lamination-type resistance element obtained by increasing the number of laminations of the second group of internal electrodes of the lamination-type resistance element shown in Fig. 4.

[0040] ——— Fig. 6 is a front sectional view of a lamination-type resistance element obtained by decreasing the number of laminations of the second group of internal electrodes of the lamination-type resistance element shown in Fig. 4.

[0041] ——— Fig. 7 is a sectional view showing a first example of a related lamination-type resistance element.

[0042] ——— Fig. 8 is a sectional view showing a second example of the related lamination-type resistance element.

#### DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

##### Numerals

21, 31, and 41	lamination-type resistance elements
23, 33, and 43	laminated sinter
24a, 24b, 34a, and 44	first internal electrodes
25a, 25b, 34b, and 45	second internal electrodes
36	internal electrode (no-connection-type internal electrode)
28, 38, and 48	gap
29, 30, 39, 40, 49, and 50	external electrodes
51	lamination-type resistance element

## Best Mode for Carrying Out the Invention

### Embodiment 1

[0043] — Fig. 1 is a sectional view of a first preferred embodiment of a lamination-type resistance element.

[0044] — A lamination-type resistance element 21 shown in Fig. 1 includes ~~1 contains~~ a laminated sinter 23 in which a plurality of NTC thermistor layers 22 as a plurality of ceramic resistance layers is laminated and integrally sintered. First internal electrodes 24a and 24b and second internal electrodes 25a and 25b are provided~~contained~~ inside the laminated sinter 23. External electrodes 29 and 30 are provided~~formed~~ on the outer surface, specifically~~concretely~~, on both end portions of the laminated sinter 23.

[0045] — The first internal electrode 24a as a first divided internal electrode and the internal electrode 25a as a second divided internal electrode are arranged~~formed~~ in such a way that one end portion of the internal electrode 24a and one end portion of the internal electrode 25a face each other on the same planar plane~~—~~ surface with a gap 26a therebetween. The other end portion of the first internal electrode 24a is electrically connected to the external electrode 29 and the other end portion of the second internal electrode 25a is electrically connected to the external electrode 30.

[0046] — Moreover, when internal electrodes on the same plane are seen as a unified electrode, the divided internal electrodes indicate one electrode separated by a gap. For example, the internal electrode 24a and the internal electrode 25a are considered as a unified electrode on the same plane

and each of the ones separated by a gap may be called a divided internal electrode 24a and a divided internal electrode 25a, respectively. Furthermore, when the internal electrode 25a and an internal electrode 24b, for example, lie on top of one another through a thermistor layer, the internal electrode 25a may be simply called an internal electrode.

[0047] —Furthermore, the first internal electrode 24b as a divided internal electrode and the second internal electrode 25b are ~~arranged~~~~formed~~ in such a way that one end portion of the internal electrode 24b and one end portion of the internal electrode 25b face each other on the same plane with a gap 26b therebetween. The other end portion of the first internal electrode 24b is electrically connected to the external electrode 29 and the other end portion of the second internal electrode 25b is electrically connected to the external electrode 30.

[0048] —The gaps 26a and 26b are disposed inside the sinter 23 so as to be next to each other along the lamination direction of the plurality of thermistors 22. Furthermore, the gaps 26a and 26b are ~~arranged~~~~formed~~ so as to be at different locations in the direction perpendicular to the lamination direction of the sinter 23 and in the direction in which both end portions of the sinter 23 are connected. The above-described structure of the first internal electrodes 24a~~24a~~ and 24b corresponds to a first internal electrode group A of the present invention. Here, a resistance unit is defined by in which the two internal electrodes 24b and 24b ~~are~~ each put on top of the internal electrode 25a with a

thermistor layer as a ceramic resistance layer therebetween ~~is constituted~~. One end of the resistance unit is connected to the first external electrode 29 and the other end is connected to the second external electrode 30. Moreover, in the present preferred embodiment, the internal electrodes 24b and 24b and the internal electrode 25a~~24a~~, that is, the three internal electrodes, are put on top of one another with thermistor layers disposed therebetween~~thereamong~~ in the above-described resistance~~resistant~~ unit of the first internal electrode group A. ~~But, but~~, in the present preferred embodiment~~invention~~, since it is sufficient to have at least two internal electrodes facing each other through a ceramic resistance layer, the number of laminations of internal electrodes facing each other through a ceramic resistance layer is not particularly limited.

[0049] —The lamination-type thermistor 21 further includes~~contains~~ the following structure. That is, a second internal electrode group B is provided~~formed~~ above the first internal electrode group A ~~of the~~ inside the sinter 23.

[0050] —The second internal electrode group B has the following structure. Third internal electrodes 27a and fourth internal electrodes 27b are provided~~contained~~ inside the laminated sinter 23 in which the plurality of thermistor layers 22 are integrally sintered. The third internal electrodes 27a and the fourth internal electrodes 27b are arranged~~formed~~ in such a way that one end portion of the internal electrode 27a and one end portion of the internal electrode 27b face each other on the same plane with a gap 28

therebetween. The other end portion of the third internal electrode 27a is electrically connected to the external electrode 29 and the other end portion of the fourth internal electrode 27b is electrically connected to the external electrode 30.

[0051] —The gaps 28 of the second internal electrode group B are provided~~formed~~ at the same location, when seen from one end side of the lamination direction of the plurality of thermistor layers 22, for example, from the upper, inside of the laminated sinter 23. Furthermore, the gaps 28 are provided~~formed~~ at a different location from the gap 26a of the first internal electrode group A when seen from one end side in the lamination direction of the thermistor layers, more specifically~~concretely~~, at a different location in the direction connecting both end portions of the laminated sinter 23. Moreover, in the second internal electrode group B shown in Fig. 1, three sets of electrodes made up~~formed~~ of ~~a~~-third internal electrodes ~~electrode~~-27a and ~~a~~-fourth internal electrodes ~~electrode~~-27b are put on top of one another, but the number of layers of the combination may be designed according to a target resistance value. Furthermore, in Fig. 1, the thickness of an NTC thermistor layer 22a existing between the first internal electrode group A and the second internal electrode group B is preferably larger than the thickness of the other NTC thermistor layers 22, but the thickness may also be made the same.

[0052] —In the lamination-type resistance element according to the first preferred embodiment, the resistance

value is determined in the following way. That is, in the first internal electrode group A, the resistance value is determined by the size of the gaps 26a and 26b ~~formed~~ between the first internal electrodes 24a and 25a and between the second internal electrodes 24b and 25b, respectively, and by the overlapping area and space between the first internal electrode 24a and the second internal electrode 25b. Moreover, in the second internal electrode group B, the resistance value is determined by the size of the gaps 28 ~~formed~~ between the third internal electrodes 27a and the fourth internal electrodes 27b. Accordingly, the resistance value of the lamination-type resistance element becomes a composite resistance value of the resistance values of the first internal electrode group A and the second internal electrode group B. In the second internal electrode group B, although the resistance value is determined by the size of the gap 28, the resistance~~resonance~~ value produced~~formed~~ by the gap 28 is small.

[0053] —Furthermore, in the first preferred embodiment, since three sets of ~~an~~-internal electrodes 27a and ~~an~~-internal electrodes ~~electrode~~-27b are laminated in the second internal electrode group B, the three gaps 28 are next to each other in the lamination direction of the thermistor layers 22 and disposed so as to lie on top of one another when seen from one end side in the lamination direction. That is, the gaps 28 and 28 face each other through one thermistor layer 22. In this way, since a plurality of gaps 28 is disposed in the second internal electrode group B and the plurality of gaps

are disposed so as to lie on top of one another, not only is the resistance value ~~created~~<sup>formed</sup> by the size of one gap 28 small, but the resistance value of the second internal electrode group B determined by the space between the plurality of gaps 28 is also small. Accordingly, it becomes possible to make fine adjustment of the resistance value of the whole lamination-type resistance element by means of the second internal electrode group.

[0054] —Moreover, in the lamination-type thermistor 21 of the first preferred embodiment, not only can fine adjustment of the resistance value be made in the above-described way, but also there is an advantage in that fine adjustment of the resistance value can be made more precisely. That is, in the lamination-type thermistor 21 of the first preferred embodiment, the gap 26b between a first internal electrode 24b and a second internal electrode 25b of the first internal electrode group and the gap 28 between a third internal electrode 27a and a fourth internal electrode 27b of the second internal electrode group are disposed so as to be at the same location, that is, to lie on top of one another when seen from the lamination direction, the gap 26b and the gap 28 being next to each other through the thermistor layer 22a. In order to show this more clearly, in Fig. 1, reference characters X and Y are given to the gaps which can be made close to each other at the same location when seen from the above-described lamination direction.

[0055] —As is clear in Fig. 1, the gap X, ~~the~~ closest to the second internal electrode group of, ~~in~~ the gaps 26b of 26a

~~in~~ the first internal electrode group, and the gap Y, ~~the~~  
closest to the first internal electrode group of, ~~in~~ the gaps  
28 of ~~in~~ the second internal electrode group, are  
~~arranged~~formed at the same location when seen from the  
lamination direction.

[0056] — This means that the first internal electrode 24b  
and the second internal electrode 25b for ~~defining~~constituting  
the gap X can be made in the same shape as the third internal  
electrode 27a and the fourth internal electrode 27b for  
~~defining~~constituting the gap Y. In the present preferred  
embodiment, since the internal electrode pattern on the upper  
surface of the thermistor layers 22 is the same as the  
internal electrode pattern on the lower surface and the gaps X  
and Y are at the same location when seen from one end side in  
the lamination direction, fine adjustment of the resistance  
value can be made more precisely. This is because the inner  
ends of the internal electrodes 24b and 25b  
~~defining~~constituting the gap X in the first internal electrode  
group and the inner ends of the third and fourth internal  
electrodes 27a and 27b ~~defining~~constituting the gap Y in the  
second internal electrode group are uniform in location and  
accordingly the current path becomes uniform and variations of  
the resistance value can be more reduced.

[0057] — Accordingly, ~~preferably,~~ when the first internal  
electrode group and the second internal electrode group are  
disposed in parallel in the lamination direction and the  
above-described gaps are ~~provided~~contained in the internal  
electrodes close to each other in the first internal electrode



group and the second internal electrode group, it is desirable to dispose the gaps at the same location when seen from the lamination direction, that is, to dispose the gaps so as to lie on top of one another.

[0058] —However, in the present preferred embodiment, it is not necessarily required to put the second internal electrode group above or below the first internal electrode group in parallel, and the first internal electrode group may be disposed in the portion where the second internal electrode group is provided.

#### Embodiment 2

[0059] —Fig. 2 is a sectional view of a second preferred embodiment of the lamination-type resistance element.

[0060] —A lamination-type resistance element 31 preferably includes a laminated sinter 33 in which a plurality of NTC thermistor layers 32 is laminated and integrally sintered. First internal electrodes 34a and second internal electrodes 34b are included in the laminated sinter 33. Furthermore, an internal electrode 36 is arranged so as to face the first internal electrodes 34a and the second internal electrodes 34b through a thermistor layer 32. External electrodes 39 and 40 are provided on the external surface of the laminated sinter 33, specifically, at both end portions.

[0061] —One end portion of the first internal electrode 34a as a divided internal electrode and one end portion of the second internal electrode 34b as a divided internal electrode are arranged to face each other on the same plane with a

gap 35 therebetween inside the laminated sinter 33. The other end portion of the first internal electrode 34a is electrically connected to the external electrode 39 and the other end portion of the second internal electrode 34b is electrically connected to the external electrode 40.

[0062] —The internal electrode 36, in which both end portions are not ~~extended~~ to the external surface of the laminated sinter 33, is a no-connection-type internal electrode not electrically connected to the external electrodes 39 and 40. The structure having the first internal electrodes 34a, the second internal electrodes 34b, and the no-connection-type internal electrode 36 corresponds to first internal electrode group C of the present preferred embodiment.

[0063] —Moreover, in the first internal electrode group C, the first internal electrodes 34a and second internal electrodes 34b and the no-connection-type internal electrode 36 lie on top of one another through a thermistor layer. That is, a resistance unit having the internal electrodes 34a and 34b and the no-connection-type internal electrode 36 is ~~produced, constituted,~~ One end of the resistance unit is connected to the first external electrode 39 and the other end is connected to the second external electrode 40.

[0064] —Furthermore, also in the present preferred embodiment, it is sufficient to have at least two internal electrodes disposed so as to lie on top of one another with a thermistor layer therebetween, that is, it is sufficient that the number of ceramic resistance layers sandwiched by internal

electrodes is one or more and the number is not restricted in particular.

[0065] —The lamination-type thermistor 31 further ~~includes~~~~contains~~ the following structure. That is, a second internal electrode group D is ~~provided~~~~formed~~ inside the laminated sinter 33 so as to be close to the first internal electrode group C.

[0066] —The second internal electrode group D ~~includes~~~~contains~~ the following structure. Third internal electrodes 37a and fourth internal electrodes 37b are ~~included~~~~contained~~ inside the laminated sinter 33 in which a plurality of thermistor layers 32 are laminated and integrally sintered. One end portion of ~~a the~~ third internal electrode 37a and one end portion of ~~a the~~ fourth internal electrode 37b face each other on the same plane with a gap 38 therebetween inside the laminated sinter 33. The other end portion of the third electrode 37a is electrically connected to the external electrode 39 and the other end portion of the fourth electrode 37b is electrically connected to the external electrode 40.

[0067] —The gaps 38 of the second internal electrode group D are ~~arranged~~~~formed~~ at the same location along the lamination direction of the plurality of thermistor layers 32 inside the laminated sinter 33. The gaps 38 shown in Fig. 2 are ~~arranged~~~~formed~~ so as to be substantially at the same distance from both end portions of the laminated sinter 33, that is, to be located substantially in the middle. Furthermore, the gaps 38 are ~~preferably arranged~~~~formed~~ at the same location as the gaps 35 of the first internal electrode

group C when seen from the lamination direction of the thermistor layers 32, more ~~specifically~~concretely, at the same location in the direction of the connection of both end portions of the laminated sinter 33, but the gaps 38 may be ~~arranged~~formed at different locations. Furthermore, in the second internal electrode group D shown in Fig. 2, although the third internal electrodes 37a and the fourth internal electrodes 37b are ~~provided~~formed in three layers, the number of layers may be designed according to the target resistance value. Furthermore, in Fig. 2, although the thickness of the NTC thermistor layers 32a existing between the first internal electrode group C and the second internal electrode group D is ~~preferably made~~larger than the thickness of the other NTC thermistor layers 32, the thickness may be made the same.

[0068] —In the lamination-type resistance element according to the second preferred embodiment, the resistance value is determined in the following way. That is, in the first internal electrode group C, the resistance value is determined by the size of the gap 35 ~~between~~formed by the first internal electrode 34a and the second internal electrode 34b, the overlapping area between the first internal electrode 34a and the no-connection-type internal electrode 36 and the space between the both, and the overlapping area between the second internal electrode 34b and the no-connection-type electrode 36 and the space between the both. Furthermore, in the second internal electrode group D, the resistance value is determined by the size of the gap 38 ~~between~~formed by the third internal electrode 37a and the fourth internal electrode

37b. Accordingly, the resistance value of the lamination-type resistance element becomes a composite resistance value of the resistance values of the first internal electrode group C and the second internal electrode group D. In the second internal electrode group D, although the resistance value is determined by the size of the gap 38, a plurality of gaps 38 is at neighboring locations along the lamination direction of the thermistor layers and ~~arranged~~~~formed~~ at the same location, and the resistance value determined by the size of the gap 38 is small. Accordingly, fine adjustment of the resistance value of the whole of the lamination-type resistance element becomes possible by means of the second internal electrode group D.

#### Embodiment 3

[0069] ——— Fig. 3 is a sectional view of a third preferred embodiment of the lamination-type resistance element.

[0070] ——— In a lamination-type resistance element 41 shown in Fig. 3, first internal ~~electrodes 44 and second internal electrodes 44 and second internal electrodes 45~~ are ~~provided~~~~formed~~ inside a laminated sinter 43 in which a plurality of NTC thermistor layers 42 are laminated and integrally sintered. External electrodes 49 and 50 are ~~provided~~~~formed~~ on the outer surface, ~~specifically~~~~concretely~~, in both end portions of the laminated sinter 43.

[0071] ——— The first internal electrode 44 and the second internal electrode 45 are ~~arranged~~~~formed~~ so that one end portion of each electrode may extend to one end portion of the laminated sinter 43. The other end portion of the first internal electrode 44 is electrically connected to the

external electrode 49 and the other end portion of the second internal electrode 44 is electrically connected to the external electrode 50. The structure ~~formed~~ of the ~~above~~ first internal electrodes 44 and 45 corresponds to the first internal electrode group E of the present preferred embodiment.

[0072] —In the present preferred embodiment, in the first internal electrode group E, a plurality of internal electrodes 44 and 45 are disposed so as to lie on top of one another through a thermistor layer as a ceramic resistance layer. A resistance unit having the plurality of internal electrodes 44 and 45 is produced~~constituted~~, and one end of the resistance unit is connected to the external electrode 49 and the other end is connected to the external electrode 50.

[0073] —Moreover, the number of laminations of the internal electrodes lying on top of one another with a thermistor layer therebetween, which defines~~constitutes~~ the above resistance unit, is not limited to four as shown in Fig. 4. That is, it is sufficient that at least two internal electrodes are disposed so as to lie on top of one another with a thermistor layer therebetween. That is, the number of ceramic resistance layers, which are~~for taking out the resistance value~~ sandwiched between internal electrodes, for taking out the resistance value, may be ~~any number of~~ one or more.

[0074] —The lamination-type thermistor 41 further includes~~contains~~ the following structure. That is, a second internal electrode group F is provided~~formed~~ next to the first

internal electrode group E inside the laminated sinter 43.

[0075] —The second internal electrode group F has the following structure. Third internal electrodes 47a and fourth internal electrodes 47b are provided~~formed~~ inside the laminated sinter 43 in which the plurality of thermistor layers 42 are laminated and integrally sintered. The third internal electrodes ~~electrode~~ 47a and the fourth internal electrodes 47b are arranged~~formed~~ in such a way that one end portion of an ~~the~~ electrode 47a and one end portion of an ~~the~~ electrode 47b face each other on the same plane with a gap 48 therebetween inside the laminated sinter 43. The other end portion of the third internal electrode 47a is electrically connected to the external electrode 49 and the other end portion of the fourth internal electrode 47b is electrically connected to the external electrode 50.

[0076] —A plurality of gaps 48 of the second internal electrode group F is provided~~formed~~ inside the laminated sinter 43 in such a way that the gaps 48 are next to each other along the lamination direction of the plurality of thermistor layers 42 and at the same location when seen from the lamination direction. The gaps 48 shown in Fig. 3 are arranged~~formed~~ so as to be close to the external electrode 50. Moreover, in the second internal electrode group F shown in Fig. 3, although the third internal electrode 47a and the fourth internal electrode 47b are provided~~formed~~ in three layers, it is sufficient that they are provided~~formed~~ so as to have at least two layers.

[0077] —In the lamination-type resistance element

according to the third preferred embodiment, the resistance value is determined in the following way. That is, in the first internal electrode group E, the resistance value is determined by the overlapping area of the first internal electrode 44 and the second internal electrode 45 and the space between the internal electrodes 44 and 45. Moreover, in the second internal electrode group F, the resistance value is determined by the gap 48 ~~between~~~~formed by~~ the third internal electrode 47a and the fourth internal electrode 47b. Accordingly, the resistance value of the lamination-type resistance element becomes a composite resistance value of the first internal electrode group E and the second internal electrode group F. In the second internal electrode group F, the resistance value is determined by the size of the gaps 48. The gaps are positioned so as to be next to each other in the lamination direction of the thermistor layers 42 and to be at the same location when seen from the lamination direction. The resistance value given by the size of the plurality of gaps 48 is small. Accordingly, it becomes possible to make fine adjustment of the whole resistance value of the lamination-type resistance element by means of the second internal electrode group F.

[0078] ———Next, it is more specifically~~concretely~~ described that, when the lamination-type resistance element of the present preferred embodiment~~invention~~ is used, it is possible to make fine adjustment of the resistance value by increasing or decreasing the number of laminated layers of the second internal electrode group.



[0079] — Fig. 4 is a front sectional view of a lamination-type thermistor 51 according to a modified example of the resistance thermistor 31 of the preferred embodiment shown in Fig. 2. The lamination-type thermistor 51 is the same as the lamination-type thermistor 31 except that the first internal electrode 34a and the second internal electrode 34b in the uppermost layer shown in Fig. 2 are not ~~provided, contained.~~ Accordingly, the same reference numerals ~~are numeral is given to the same elements, portion~~ and the description ~~thereof for Fig. 2 is omitted.~~

[0080] — It is now assumed that a lamination-type thermistor 51 having a resistance value of  $47,000\ \Omega$  in design as shown in Fig. 4 is manufactured by way of experiment using a specific thermistor material, for example. However, practically there are variations in the thermistor material to be used and the resistance value of the obtained lamination-type thermistor 51 may vary. For example, when the resistivity of the thermistor material is high, the resistance value becomes higher than  $47,000\ \Omega$ . For example, when the resistance value is about  $47,734\ \Omega$ , it is sufficient to increase the number of pairs of internal electrodes by one regarding the second internal electrode group as shown in Fig. 5. In this way, the resistance value can be reduced by about 4.0% by increasing the number of pairs of electrodes provided ~~informed of~~ the third and fourth internal electrodes of the first internal electrode group by one.

[0081] — Furthermore, when the resistivity of the thermistor material to be used becomes smaller, the

lamination-type thermistor 51 having a resistance value lower than the target resistance value can be obtained. That is, when the lamination-type thermistor 51 shown in Fig. 4 is manufactured by way of experiment and the resistance value becomes about 45,825  $\Omega$ , it is sufficient to reduce the number of pairs of electrodes provided informed of the third and fourth internal electrodes 37a and 37b in the first internal electrode group by one to result in two as shown in Fig. 6. In this case, it is possible to increase the resistance value by about 2.5% and, as a result, it is possible to achieve/realize the target resistance value of 47,000  $\Omega$ .

[0082] —As described above, in the lamination-type resistance element of the present preferred embodiments/invention, it is understood that fine adjustment of the resistance value can be performed by increasing or decreasing the number of pairs of electrodes provided informed of the third and fourth internal electrodes in the first internal electrode group. When the number of pairs of electrodes increases, very fine adjustment of the resistance value can be performed, such as a change in the resistance value of about 0.5%, for example. Accordingly, it is understood that very fine adjustment of the resistance value over a wide range can be performed by changing the number of laminations of electrodes.

[0083] —In each lamination-type resistance element in the above-described preferred embodiments-1, 2, and 3, an example of an NTC thermistor is shown, but the lamination-type resistance element can be applied to PTC thermistors.

[0084] While preferred embodiments of the present invention have been described above, it is to be understood that variations and modifications will be apparent to those skilled in the art without departing the scope and spirit of the present invention. The scope of the present invention, therefore, is to be determined solely by the following claims.